

POLIAX D EN 12115

According to EN 12115

Suitable for delivery of highly aggressive chemicals, according to EN 12115,

Hose Construction

Tube: Black, smooth antistatic EPM nitrosamine free rubber compound

Reinforcement: Synthetic textile fabrics and built-in copper wires to facilitate the electrical connection between hose and end couplings

Cover: Black, antistatic ($R < 1 \text{ M}\Omega/\text{m}$), EPDM rubber compound, heat, abrasion, ageing and weather resistant



- In-plant and storage tank transfer
- Nitrosamine free
- Suitable for ATEX areas
- Meets TRbF 131 part 2 par 5.5 (flame resistance)
- Burst Pressure Value 4:1



Tolerances

According to EN 12115

Refer to Technical Handbook on page TH34

Temperature Range

-35 °C (-31 °F) to +100 °C (+212 °F)

For aggressive chemicals and solvents the hose is intended to be used at room temperature. The hose can be cleaned and sterilized with usual detergents or steam – a temperature of +130 °C (+266 °F) for short periods.

Part Number	I.D. (mm)	O.D. (mm)	Working Pressure			Weight kg/m	min. Bend Radius mm	in Stock
			MPa	psi	bar			
IH36810130/40	19	31	1.6	232.0	16	0.56	125	Y
IH36810131/40	25	37	1.6	232.0	16	0.71	150	Y
IH36810132/40	32	44	1.6	232.0	16	0.86	175	Y
IH36810133/40	38	51	1.6	232.0	16	1.11	225	Y
IH36810134/40	50	66	1.6	232.0	16	1.72	275	Y
IH36810135/40	63.5	79	1.6	232.0	16	2.10	300	N
IH36810136/40	75	91	1.6	232.0	16	2.56	350	N
IH36810137/40	100	116	1.2	180.0	12	3.38	450	N

WARNING!

If delivering chemicals over +25 °C (+77 °F), please contact us. Many chemical products can cause severe injuries to people or damage to property, and here are risks of environmental pollution in case of leakage or hose burst. All necessary measures must be taken in order to avoid accidents both during normal service operations and during hydrostatic tests, which must be carried out by trained personnel using suitable tools.

POLIAX D EN 12115:2011 - EPDM - D - I.D. - WP ...bar -

Q - TRbF 131 T2p. 5.5 - Quarter/Year

Parker DE IN ITALY

Distributed by:



Bulgaria
Telephone: +359 2 973 27 67
Fax: +359 2 973 26 65
E-mail: office@daisglobal.eu
Web: http://markuchi.eu/

România
Telephone/Fax : +40 21 780 45 58
E-mail: office_ro@opwmarket.com
Web: http://furtunuri.eu/

Srbija
Telephone/Fax : 038111/2619-200
E-mail: office_sr@opwmarket.com
Web: http://creva.eu/