POLIAX UPE CON SM OND EN 12115

According to EN 12115

POLIAX UPE CON SM EN 12115 OND is a very flexible hose suitable for suction and delivery of a wide range of highly aggressive chemicals such as most industrial acids, alkalis, oils, fuels and solvents. It can also be used as a flexible connections in paint plants.

Refer to the Chemical Resistant Chart to determine compatibility with specific chemi cals. For severe or special applications - for tighter bending radius - or if in doubt, please ask our Technical Assistance.

Hose Construction

Tube: Lucent, black, smooth, conductive,

> ultra high molecular weight polyethylene (UHMWPE), suitable for foodstuff contact according to FDA,

EEC Directive, Italian Decrees

Reinforcement: Synthetic textile fabrics, embedded

> steel wire helix and built-in copper wires to allow the electrical connec tion between hose and couplings

Cover: Black, corrugated, antistatic

> $(R < 1 M\Omega/m)$, EPDM rubber com pound, heat, abrasion, ageing and

weather resistant



- Extreme flexibility, superior kink resist ance, minimal force to bend
- Fits also foodstuffs according to FDA
- · Suitable for ATEX areas
- Meets TRbF 131 part 2 par 5.5 (flame resistance)
- Vacuum: 0.9 bar up to dn 63.5, for larger sizes 0.8 bar
- Burst Pressure Value 4:1

Temperature Range

-20 °C (+5 °F) to +100 °C (+212 °F)

For aggressive chemicals and solvents the hose is intended to be used at room temperature. The hose can be cleaned and sterilized with usual detergents or steam - a temperature of +130 °C (+266 °F) for short periods.

Tolerances

According to EN 12115

Refer to Technical Handbook on page TH34

Part Number			Working Pressure			Weight	min. Bend Radius	in Stock
	I.D. (mm)	O.D. (mm)	MPa	psi	bar	kg/m	mm	
IH36811570/40	19	31	1.6	232.0	16	0.71	38	Υ
IH36811571/40	25	37	1.6	232.0	16	0.87	50	Υ
IH36811572/40	32	44	1.6	232.0	16	1.07	64	Υ
IH36811573/40	38	51	1.6	232.0	16	1.35	76	Υ
IH36811574/40	50	66	1.6	232.0	16	2.29	100	Υ
IH36811575/40	63.5	79	1.6	232.0	16	2.51	127	N
IH36811576/40	75	91	1.6	232.0	16	3.07	150	N
IH36811577/20	100	116	1.2	180.0	12	4.43	200	N

POLIAX EN 12115:2011 - UPE - SD - I.D. - WP ...bar -

 Ω - TRbF 131 T2p. 5.5 - Quarter/Year

cerADE IN ITALY

Distributed by:

