

LIBECCIO EN ISO 3861

According to EN ISO 3861

Suitable for conveying of wet and dry sand and grit blasting materials.

Hose Construction

Tube: Smooth, black, antistatic, abrasion resistant BR/NR rubber compound. Abrasion according to ISO 4649: max. 60 - 70 mm³

Reinforcement: Synthetic textile fabrics

Cover: Black, smooth, antistatic, weather and abrasion resistant SBR/NBR compound. The cover is pinpricked to prevent blistering and bubbling, max. resistance on finished hose: 2,0 MΩ/m








- Exceeds EN ISO 3861 requirements
- Robust and light version available
- Construction, general industry, shipyards
- Burst Pressure Value 4:1

Tolerances

According to RMA steel mandrel
Refer to Technical Handbook on page TH34

Temperature Range

-30 °C (-22 °F) to +70 °C (+158 °F)

Part Number	 I.D. (mm)	 O.D. (mm)	 Working Pressure			 Weight kg/m	 min. Bend Radius mm	in Stock
			MPa	psi	bar			
IH36820300/40	19	33	1.0	150.0	10	0.69	190	Y
IH36820200/40	25	40	1.0	150.0	10	0.92	250	Y
IH36820201/40	30	45	1.0	150.0	10	1.05	300	Y
IH36820202/40	32	48	1.0	150.0	10	1.37	320	Y
IH36820303/40	38	55	1.0	150.0	10	1.46	380	Y
IH36820305/40	42	60	1.0	150.0	10	1.70	420	N
IH36820206/40	50	72	1.0	150.0	10	2.54	500	Y
IH36820207/40	60	82	1.0	150.0	10	2.95	600	Y
IH36820209/20	80	105	1.0	150.0	10	4.32	800	Y
IH36820210/20	90	115	1.0	150.0	10	4.84	900	N
IH36820211/20	100	125	1.0	150.0	10	5.30	1000	Y

RUBBER HOSE LIBECCIO EN ISO 3861 ID mm – WP 1,0 MPa – BP 4,0 MPa ABRASION 60/70 mm³ MADE IN ITALY



Distributed by:



Bulgaria
Telephone: +359 2 973 27 67
Fax: +359 2 973 26 65
E-mail: office@daisglobal.eu
Web: http://markuchi.eu/

România
Telephone/Fax : +40 21 780 45 58
E-mail: office_ro@opwmarket.com
Web: http://furtunuri.eu/

Srbija
Telephone/Fax : 038111/2619-200
E-mail: office_sr@opwmarket.com
Web: http://creva.eu/