



# CARBOPRESS SAE J 30 R7

According to SAE J 30 R7

Low permeability, fire resistant hose, for lead and unleaded fuels in car and motorbike engines and gearbox lubricants where high performance and compliance to standards are important issue. Hose meets the American Standard SAE J30 R7.

## Hose Construction

Tube:	Black, smooth, antistatic (R < 1 MΩ/m) NBR rubber compound, resistant to oils, fuels and unleaded petrol with aromatic content not exceeding 50 %
Reinforcement:	Synthetic textile yarns
Cover:	Black, smooth, antistatic (R < 1 MΩ/m) CR rubber compound resistant to oils, abrasion, weather and fire



- Exceeds SAE J 30 R7 in WP
- Antistatic cover and tube compounds
- Suitable for B100 up to 70 °C
- Superior cover compound resistant to abrasion and weathering
- Burst Pressure Value 4:1

## Tolerances

According to SAE J30 R7  
Refer to Technical Handbook on page TH34

## Temperature Range

-40 °C (-40 °F) to +125 °C (+257 °F)

Part Number	I.D. (mm)	O.D. (mm)	Working Pressure			Weight kg/m	min. Bend Radius mm	in Stock
			MPa	psi	bar			
IH30872400/100	4	9.1	1.0	150.0	10	0.07	30	N
IH30872401/100	4.8	10.3	1.0	150.0	10	0.09	40	N
IH30872402/100	6.4	12.7	1.0	150.0	10	0.13	55	Y
IH30872403/100	8	14.3	1.0	150.0	10	0.16	65	Y
IH30872404/100	9.5	15.9	1.0	150.0	10	0.18	75	Y
IH30872405/100	12.7	19.9	1.0	150.0	10	0.25	100	Y

RUBBER FUEL HOSE CARBOPRESS SAE 30 R7 MADE IN ITALY

Parker spaced every 300 mm

Distributed by:



Bulgaria  
Telephone: +359 2 973 27 67  
Fax: +359 2 973 26 65  
E-mail: office@daisglobal.eu  
Web: http://markuchi.eu/

România  
Telephone/Fax : +40 21 780 45 58  
E-mail: office\_ro@opwmarket.com  
Web: http://furtunuri.eu/

Srbija  
Telephone/Fax : 038111/2619-200  
E-mail: office\_sr@opwmarket.com  
Web: http://creva.eu/